

TECHNICAL DATA SHEET

TREEHOUSE Fumed Oak White



PRODUCT DETAILS

| Product range | TREEHOUSE, engineered oak floors with a band sawn finish |
|-------------------|---|
| Available formats | Boards, herringbone, chevron |
| Sizes | Board widths: 145mm / 185mm / 225mm / 245mm / 285mm / 300mm |
| | Board lengths: |
| | random between 1.5m and 2.5m (285mm and wider |
| | are produced in longer lengths) |
| | Herringbone and chevron parquet: |
| | 65 x 325mm / 85 x 425mm / 105 x 525mm / |
| | 145 x 580mm / 145 x 725mm / 185 x 925mm |
| Depth | 15mm or 20mm |
| Construction | Engineered with birch plywood base |
| Finish | Sawn and oiled with hardwax oil |
| Profile | Tongue and groove |
| Edge profile | Micro bevelled, unbevelled or hand-cut bevel |
| Wear layer | 4mm on 15mm depth |
| | 6mm on 20mm depth |
| | |
| | |
| | |

WARRANTY AND INSTALLATION

Manufacturer's warranty: 5 years, subject to terms and conditions. Note there is no warranty on the finish as we have no control over usage and aftercare. All our floors must be installed by a competent installer onto a firm, level (flat), clean and dry substrate. The site must be heated if necessary and water tight with all glazing fitted. Wet works such as plastering and tiling must be completed prior to installation.

GRADES

| Premier | Occasional, small knots up to 15mm |
|----------|--|
| Rustic A | Knots up to 40mm, including filled knots, sapwood up to 10mm |
| Rustic | Frequent knots up to max. 80mm, including filled knots and cracks up to 400mm, sapwood up to 25mm, centre core |

Premier and Rustic A grades are available in widths up to 245mm

TECHNICAL CRITERIA

| Origin | Europe |
|-----------------------|--------------------------|
| Certification | PEFC, FSC on request |
| Formaldehyde emission | E1 |
| Thermal conductivity | 0.17 W/mk for 20mm depth |
| | 0.12 W/mk for 15mm depth |

MAINTENANCE

| Initial care & re-oiling | Do not clean the floor with water in the first 4 weeks after installation We recommend a final coat of oil after installation. Re-oil every 2-5 years depending on the volume of traffic. High usage areas may need to be re-oiled annually Use Floorservice Maintenance Oil Antique White or Osmo Polyx Hardwax Oil 3044 Raw |
|--------------------------|---|
| General cleaning | Osmo Wash and Care soap for regular cleaning |
| Other | Before re-oiling clean with WOCA Wood Cleaner and leave to dry for 8 hours |

INSTALLATION METHODS

| Fixed installation | Highly recommended, either fully bonded or secretly nailed |
|-------------------------|---|
| Floating installation | Possible depending on room size and only up to a board width of 245mm |
| Over underfloor heating | This floor is compatible with UFH. Floors must be fully bonded to the substrate |
| | The temperature of the floor surface must not exceed 27 degrees. Floor sensors must be installed to monitor the maximum temperature |

Waxed Floors, 92 Battersea Rise, SW11 1EJ, London T. +44 20 7738 1620 F. +44 20 7738 1630 sales@waxedfloors.co.uk www.waxedfloors.co.uk

The company reserves the right to change this specification at any time without prior notice to third parties. The image is intended as a guide only and should not be regarded as absolutely accurate.